



COVERWORLD
UK LIMITED

COVERWORLD 15 μ LINING ENAMEL

Properties	Thermosetting Paint	<ul style="list-style-type: none">• Surface treatment and paint (free of hexavalent chromium & heavy metals)
Applications	Liners, furniture and indoor applications	
Description	Thickness	15 μ
	Composition	Front 15 μ top coat Back 5 μ backing coat
	Gloss	30 GU Other gloss levels on request
	Colours	RAL9010 (White)
	Appearance	Smooth
	Temporary Protection (optional)	Self-adhesive film
	Performance	Adhesion of the coating (T-bend)
Resistance to cracking on bending (T-bend)		≤ 3 T
Impact Resistance		15 J
Surface "pencil" hardness		HB to H
Clemen scratch resistance		≥ 1 Kg
Condensation resistance		
<ul style="list-style-type: none">• QCT test		500 Hours
<ul style="list-style-type: none">• Corrosion protection category		CP12
Salt spray test		150 Hours
Fire Behavior Classification (EN 13501-1)	A1	

DATA SHEET

roofing and cladding technology