



COVERWORLD
UK LIMITED

COVERWORLD 200µ/100µ D/SIDED PLASTISOL

DATA SHEET

Properties

- Good Corrosion Resistance
- Very Good Formability
- Excellent Abrasion Resistance
- Phthalate Free

Applications

External Uses: Construction (cladding, roofing and accessories)

Description

Thickness	200µ Exterior, 100µ Interior
Composition	Z225 Or Equivalent
	Front 200µ Of Finish
	Back 100µ Of Finish
Colours	Call Sales Office For Available Colour Range
Appearance	Embossed Leathergrain Exterior Finish Smooth Interior Finish

Performance (Exterior Coat)

Adhesion of the Coating (T-bend)	≤ 1 T
Resistance to Cracking on Bending (T-bend)	≤ 3 T
Impact Resistance	Very Good
Surface "Pencil" Hardness	4 to 6B
Corrosion Resistance	
• Salt Spray Test	700 Hours
Condensation Resistance (QCT)	
• QCT Test	700 Hours
Resistance to Acids & Bases	Good
Resistance to Solvents:	
• Aliphatic and Alcohols	Very Good
• Ketones	Low
• Aromatics	Good to Very Good
Resistance to Mineral Oils	Very Good

Guarantee

Call the Sales Office for Further Details Note the Interior Finish has no guarantee

Fire Classification

EN 13501-1 Standard Cs2d0

roofing and cladding technology