

COVERWORLD 55μ HDX

Properties	Thermosetting Paint	<ul style="list-style-type: none"> • Very good UV resistance • Excellent corrosion resistance • Very good formability & robust coating • Surface treatment and paint <i>(free of hexavalent chromium & heavy metals)</i> 																																																									
Applications	External uses in severe environments (cladding, roofing & accessories)																																																										
Description	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;">Thickness</td> <td colspan="2">55μ</td> </tr> <tr> <td>Composition</td> <td>Front</td> <td>25μ primer & 30μ top coat</td> </tr> <tr> <td></td> <td>Back</td> <td>12μ backing coat</td> </tr> <tr> <td></td> <td colspan="2">Double sided finish also available</td> </tr> <tr> <td>Gloss (Gardner 60°)</td> <td colspan="2">30 GU</td> </tr> <tr> <td></td> <td colspan="2">Other gloss levels on request</td> </tr> <tr> <td>Colours</td> <td colspan="2">Call Sales Office for available colour range</td> </tr> <tr> <td>Appearance</td> <td colspan="2">Grained</td> </tr> <tr> <td>Temporary Protection (optional)</td> <td colspan="2">Self-adhesive film</td> </tr> </table>		Thickness	55μ		Composition	Front	25μ primer & 30μ top coat		Back	12μ backing coat		Double sided finish also available		Gloss (Gardner 60°)	30 GU			Other gloss levels on request		Colours	Call Sales Office for available colour range		Appearance	Grained		Temporary Protection (optional)	Self-adhesive film																															
Thickness	55μ																																																										
Composition	Front	25μ primer & 30μ top coat																																																									
	Back	12μ backing coat																																																									
	Double sided finish also available																																																										
Gloss (Gardner 60°)	30 GU																																																										
	Other gloss levels on request																																																										
Colours	Call Sales Office for available colour range																																																										
Appearance	Grained																																																										
Temporary Protection (optional)	Self-adhesive film																																																										
Performance	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;">Adhesion of the coating (T-bend)</td> <td colspan="2">≤ 1 T</td> </tr> <tr> <td>Resistance to cracking on bending (T-bend)</td> <td colspan="2">≤ 1.5 T</td> </tr> <tr> <td>Impact Resistance</td> <td colspan="2">18 J</td> </tr> <tr> <td>Clemen scratch resistance</td> <td colspan="2">≥ 3 Kg</td> </tr> <tr> <td>Corrosion resistance:</td> <td colspan="2"></td> </tr> <tr> <td>• Salt spray test</td> <td colspan="2">700 Hours</td> </tr> <tr> <td>• Corrosion resistance category</td> <td colspan="2">RC5</td> </tr> <tr> <td>Condensation resistance (QCT)</td> <td colspan="2">1500 Hours</td> </tr> <tr> <td>Corrosion protection (interior) category</td> <td colspan="2">CP14</td> </tr> <tr> <td>UV resistance</td> <td colspan="2"></td> </tr> <tr> <td>• QUV (UVA + H2O) test (2000 Hours)</td> <td colspan="2">Δ E ≤ 2; GR ≥ 80%</td> </tr> <tr> <td>• UV resistance category</td> <td colspan="2">RUV4</td> </tr> <tr> <td>Fire Behavior Classification (EN 13501-1)</td> <td colspan="2">A1 for colour class 1 to 4 A2 for metallic colour class 5</td> </tr> <tr> <td>Resistance to acids and bases</td> <td colspan="2">Good to Very Good</td> </tr> <tr> <td>Resistance to solvents:</td> <td colspan="2"></td> </tr> <tr> <td>• Aliphatics and alcohols</td> <td colspan="2">Very Good</td> </tr> <tr> <td>• Ketones</td> <td colspan="2">Low</td> </tr> <tr> <td>• Aromatics</td> <td colspan="2">Good to Very Good</td> </tr> <tr> <td>Resistance to mineral oils</td> <td colspan="2">Very Good</td> </tr> </table>		Adhesion of the coating (T-bend)	≤ 1 T		Resistance to cracking on bending (T-bend)	≤ 1.5 T		Impact Resistance	18 J		Clemen scratch resistance	≥ 3 Kg		Corrosion resistance:			• Salt spray test	700 Hours		• Corrosion resistance category	RC5		Condensation resistance (QCT)	1500 Hours		Corrosion protection (interior) category	CP14		UV resistance			• QUV (UVA + H2O) test (2000 Hours)	Δ E ≤ 2; GR ≥ 80%		• UV resistance category	RUV4		Fire Behavior Classification (EN 13501-1)	A1 for colour class 1 to 4 A2 for metallic colour class 5		Resistance to acids and bases	Good to Very Good		Resistance to solvents:			• Aliphatics and alcohols	Very Good		• Ketones	Low		• Aromatics	Good to Very Good		Resistance to mineral oils	Very Good	
Adhesion of the coating (T-bend)	≤ 1 T																																																										
Resistance to cracking on bending (T-bend)	≤ 1.5 T																																																										
Impact Resistance	18 J																																																										
Clemen scratch resistance	≥ 3 Kg																																																										
Corrosion resistance:																																																											
• Salt spray test	700 Hours																																																										
• Corrosion resistance category	RC5																																																										
Condensation resistance (QCT)	1500 Hours																																																										
Corrosion protection (interior) category	CP14																																																										
UV resistance																																																											
• QUV (UVA + H2O) test (2000 Hours)	Δ E ≤ 2; GR ≥ 80%																																																										
• UV resistance category	RUV4																																																										
Fire Behavior Classification (EN 13501-1)	A1 for colour class 1 to 4 A2 for metallic colour class 5																																																										
Resistance to acids and bases	Good to Very Good																																																										
Resistance to solvents:																																																											
• Aliphatics and alcohols	Very Good																																																										
• Ketones	Low																																																										
• Aromatics	Good to Very Good																																																										
Resistance to mineral oils	Very Good																																																										