

COVERWORLD 15 μ PERFORATED LINING ENAMEL

DATA SHEET

Properties Thermosetting Paint • Surface treatment and paint
(free of hexavalent chromium & heavy metals)

Applications **Internal lining applications where sound reduction is required.**

Description	Thickness	15 μ
	Composition	Front 15 μ top coat Back 5 μ backing coat
	Gloss	30 GU Other gloss levels on request
	Colours	RAL9010 (White)
	Appearance	Smooth
	Temporary Protection (optional)	Not applicable

Performance (Pre Perforating)	Adhesion of the coating (T-bend)	≤ 2 T
	Resistance to cracking on bending (T-bend)	≤ 3 T
	Impact Resistance	15 J
	Surface "pencil" hardness	HB to H
	Clemen scratch resistance	≥ 1 Kg
	Condensation resistance	
	• QCT test	500 Hours
	• Corrosion protection category	CP12
	Salt spray test	150 Hours
Fire Behavior Classification (EN 13501-1)	A1	

Perforations	Pattern type	R3T5
	Hole	
	• Hole type	R (Round)
	• Hole size	3mm
	Pitch	
	• Pitch type	T (Triangular)
	• Pitch size	5mm
Open Area	32.7%	

